

Sika® MonoTop®-910 N

Bonding Primer and Reinforcement Corrosion Protection

Product Description Sika® MonoTop®-910 N is a cementitious, polymer modified one-component coating material containing silica fume used as bonding primer and reinforcement corrosion protection for reinforcement. Sika® MonoTop®-910 N meets the requirement of EN 1504-7

Uses

- Suitable for control of anodic areas (Principle 11, method 11.1 of EN 1504-9)
- Suitable as a bonding primer on concrete and mortar
- Suitable in concrete repair as reinforcement corrosion protection

Characteristics / Advantages

- Easy to mix, just add water
- User-friendly application
- Excellent adhesion to concrete and steel
- Good resistance to water and chloride penetration
- Good mechanical strengths
- Can be brushed on or applied using spray gun

Product Data

Form

Appearance / Colour grey powder

Packaging 10 kg plastic pail

Storage

Storage Conditions / Shelf-Life 12 months from date of production if stored properly in undamaged original sealed packaging, in dry cooled conditions between +5°C and +35°C.

Technical Data

Chemical Base Portland cement, silica fume, re-dispersible polymer powder, selected aggregates and additives

Density: (EN 1290) Fresh mortar density: ~2.0 kg/l

Mechanical / Physical Properties

Compressive Strength (AS 1478.2) ~45 - 55 N/mm² after 28 days

Flexural Strength ~5.5 - 7.5 N/mm² after 28 days

Adhesive Bond ~2.0 - 3.0 N/mm² after 28 days

Construction



System Information

System Structures

Sika® MonoTop®-910 N is part of the Sika® Repair System complying with the relevant part of European Standard EN 1504 and comprising of :

| | |
|-------------------------|---|
| Sika® MonoTop®-910 N: | Bonding primer and reinforcement corrosion protection |
| Sika® MonoTop®-352 NFG: | Structural light weight repair mortar |
| Sika® MonoTop®-412 NFG: | Structural repair mortar |
| Sika® MonoTop®-723 N: | Pore sealer and levelling mortar |

Application Details

Consumption

Bonding Primer

This depends on the substrate roughness and thickness of layer applied. As a guide, ~1.5 – 2.0 kg of powder per m² per mm thick.

Reinforcement Corrosion Protection

As a guide, ~2.0 kg of powder per m² for 1mm layer thickness (in total min 2 layers)

Substrate quality

Concrete

The concrete shall be free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials.

Steel reinforcement

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed

Substrate Preparation

Concrete:

Delaminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means.

The surface shall be thoroughly pre-wetted and not be allowed to dry before application of the bonding primer. The surface shall achieve a dark matt appearance without glistening and surface pores and pits shall not contain water.

Steel reinforcement:

Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to SA 2 to ISO 850101



| | |
|--|---|
| Application Conditions / Limits | |
| Substrate Temperature | min. +5°C; max. +30°C |
| Ambient Temperature | min. +5°C; max. +30°C |
| Application Instructions | |
| Mixing Ratio | <p><i>For brush application</i></p> <p>2.1 litre water per 10kg bucket</p> <p><i>for spraying application</i></p> <p>2.0 litre water per 10kg bucket</p> |
| Mixing | <p>Sika® MonoTop®-910 N can be mixed with a low speed (<500 rpm) electric drill mixer. In small quantity, Sika MonoTop-910 N can also be mixed by hand.</p> <p>Pour the water in the correct proportion into a suitable mixing container. While stirring slowly, add the powder to the water. Mixed thoroughly to the required consistency (brushable non-dripping consistency).</p> |
| Application Method | <p><i>As a bonding primer</i></p> <p>Apply by brush, roller or suitable spraying equipment to the prepared (pre-wetted) substrate. To achieve good bond, Sika® MonoTop®-910 N must be applied well into the substrate, filling all unevenness.</p> <p>Subsequent repair mortar must be applied while the bonding primer is still wet.</p> <p><i>As reinforcement protection</i></p> <p>Apply first layer approx. 1.0 mm thick, using medium hard brush or spray gun to cleaned reinforcement. When first coat is hard to the finger nail, for guidance~4 to 5 hours at 20°C, apply second layer approximately 1.0 mm thick.</p> |
| Cleaning of Tools | Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed. |
| Pot-Life | ~90-120 minutes at +23°C |
| Notes on Application / Limits | <ul style="list-style-type: none"> ■ Refer to the Method Statement for Concrete Repair using Sika® MonoTop® system for more information regarding substrate preparation or refer to the recommendations provided in EN 1504-10 ■ Avoid application in direct sun and/or strong wind and/or rain. ■ Do not add water over recommended dosage. ■ Apply only to sound, prepared substrates. |
| Curing Details | |
| Curing Treatment | Protect the fresh mortar from rain while the material has not yet set. |
| Value Base | All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. |
| Health and Safety Information | |
| Important notes | <p>For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.</p> <p>Residues of material must be removed according to local regulations. Fully cured material can be disposed of as household waste under agreement with the responsible local authorities.</p> <p>Detailed health and safety information as well as detailed precautionary measures e.g. physical, toxicological and ecological data can be obtained from the safety data sheet.</p> |



Important Notification

The information, and, in particular, the recommendations relating to the application and end-use of Sika's products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject of our terms and conditions of sale. Users should always refer to the most recent issue of the Australian version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

PLEASE CONSULT OUR TECHNICAL DEPARTMENT FOR FURTHER INFORMATION.



Sika Australia Pty Limited
ABN 12 001 342 329

Tel: 1300 22 33 48
aus.sika.com

